



OGIO®
Endurance Nexus 1/4 Zip - OE335

Product Features:

- 9.3-oz, 88/12 polyester/spandex smart jersey with peaching
- 6.8-oz, 92/8 polyester/spandex air vent mesh panels
- Stay-fresh wicking technology
- Reflective taping along the side of zipper and self-fabric chin guard
- Reflective heat transfer at back neck
- Reflective **ENDURANCE** at front lower right hem
- Reflective dot matrix pattern at center back mid-waist and sleeve hem
- Flat lock seams with contrast border stitch
- Reverse coil ¼ zip with auto lock zipper pull
- Open hem with double needle hem stitch
- Open cuff with thumbholes

Adult sizes XS – 4XL

Comparable style:

OE330 - Endurance Nexus Crew


LOE330 - Endurance Nexus Ladies' V-Neck

Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference

Blacktop	Electric Blue	Gear Grey	Pace Yellow
426C	2945C	Cool Grey 11C	Between 802U & 803U (Neon Series)

Fabric Features / Detail:



OE335 - OGIO® Endurance Nexus 1/4 Zip

GARMENT MEASUREMENTS

Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest - Half Measure	17 1/2"	19"	20 1/2"	22"	23 1/2"	25"	27"	29"
Chest - Full Measure	35"	38"	41"	44"	47"	50"	54"	58"
Body Length from HPS	27 1/2"	28 1/2"	29 1/2"	30 1/2"	31 1/2"	32 1/2"	33"	33 1/2"
Sleeve Length from CB	33 1/4"	34"	34 3/4"	35 1/2"	36 1/4"	37"	37 3/4"	38 1/2"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

ADULT General Sizing Guide

Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest	30"-32"	34"-36"	38"-40"	42"-44"	46"-48"	50"-52"	54"-55"	56"-57"
Waist	26"-29"	29"-32"	32"-35"	35"-38"	38"-41"	41"-44"	44"-47"	47"-50"
Sleeve Length-CB	31"-32"	32"-33 1/2"	34"-35"	35"-36"	36"-37"	37"-38"	38"-39"	38 1/2"-39"



DECORATING INSTRUCTIONS FOR POLYESTER PERFORMANCE FABRICS

Due to the nature of polyester performance fabrics, special care must be taken throughout the decoration process. Here are some tips to effectively decorate our performance products.

- Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.
- Dryer temperature and belt speeds must be changed accordingly for polyester fabric.
- If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.
- **Screen Printing:** These garments require the use of poly inks that cure at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.
- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.
- **Heat Transfers:** Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light coloured fabric. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- **Sublimation Printing:** As noted for the poly mark heat transfers, this process can only be done on white or very light coloured fabric. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.
- A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.